

M.H

PCT


WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B01D 39/20	A1	(11) International Publication Number: WO 00/10685 (43) International Publication Date: 2 March 2000 (02.03.00)
(21) International Application Number: PCT/US99/19153 (22) International Filing Date: 24 August 1999 (24.08.99) (30) Priority Data: 60/097,687 24 August 1998 (24.08.98) US (71) Applicant (for all designated States except US): PALL CORPORATION [US/US]; 2200 Northern Boulevard, East Hills, NY 11548-1209 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): LOVE, Charles [US/US]; 4200 Old Homestead Road, Syracuse, NY 13215 (US). REKCZIS, Keith [US/US]; 19 East Garfield Street, Cortland, NY 13045 (US). HOPKINS, Scott [US/US]; 13 Hilton Road, Dryden, NY 13053 (US). (74) Agent: BELZ, John, M.; Leydig, Voit & Mayer, Ltd., 700 Thirteenth Street, N.W., Suite 300, Washington, DC 20005 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: POROUS STRUCTURES AND METHODS AND APPARATUS FOR FORMING POROUS STRUCTURES**(57) Abstract**

A porous element is produced from a slurry of inorganic (metallic) particles. Part of the liquid is removed by compression followed by drying and sintering the green body. The product is usable as inorganic filter medium.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

POROUS STRUCTURES AND METHODS AND APPARATUS FOR FORMING POROUS STRUCTURES

Background of the Invention

Inorganic filters have a number of advantages over other types of filters, such as
5 polymeric filters. Since inorganic materials such as metals are generally more heat and
chemical resistant than organic materials such as polymers, inorganic filter media can be
used in applications where polymeric filter media cannot be used. For example, a metal
filter can be used to separate fine catalytic particles from a hot gaseous stream or separate
contaminants from a hot stream of polymeric liquid. On the other hand, many polymer-
10 based filter media will degrade from the heat of such hot fluid streams. In addition,
inorganic filters can be more cost effective than polymeric filters. For example,
inorganic filters can be reused in applications where polymeric filters cannot. A metallic
filter medium can be sterilized and reused after filtering fluids, such as biological fluids.
In contrast, many polymeric filters cannot be sterilized for reuse, because most polymers
15 are not suitable for high temperature sterilization. Lastly, inorganic filters can be used to
filter high pressure fluid streams. Inorganic filters generally have greater structural
stability than polymeric filters.

Inorganic filter media, especially metallic filter media, have frequently been used
as "point of use filters". Such filters can be used to filter process fluids, e.g., fluids such
20 as etchants used to process articles) and are typically used upstream of the processed
article. In semiconductor manufacturing processes, highly pure fluids such as silane are
used. If these process fluids are not highly pure at the point of use, contaminants in the
process fluids can deposit onto a semiconductor or semiconductor precursor and damage it

(e.g., by causing a defective circuit). Damaged semiconductors are typically reworked or discarded as scrap.

Organic filter media have been described as effective for removing particulate contaminants from process fluids. However, organic filter media can unfavorably exhibit particle shedding, organic desorption (e.g., outgassing or leaching of extractables), clogging, thermal degradation and chemical degradation. Point of use filters incorporating some metallic filter media have alleviated some of these problems. However, conventional metallic filter media also have disadvantages including poor contaminant retention properties, low voids volumes, low ductility, and/or a high pressure drop.

Further, some conventional methods of manufacturing inorganic filter media are difficult, inconvenient, and expensive.

Air laying is one conventional process of forming a porous metallic filter medium. In this process, metallic powder falls under the influence of gravity into a mold. If the desired filter medium and the corresponding molding apparatus are large, the powder must be dispensed from high above the mold. Once in the mold, the powder is "fluffed up" and then compressed. The compressed powder is then sintered together to form a metal filter medium.

Conventional air-laying processes have a number of disadvantages. First, conventional air-laying processes are likely to be incapable of producing a uniformly porous medium, especial a uniformly porous non-planar filter medium. For example, a seamless filter medium with horizontal and vertical portions could be formed from a mold having corresponding horizontal and vertical surfaces. While air-laid metallic powder might be able to deposit uniformly on the horizontal surface of the mold, the air-laid

metallic powder would not be able to deposit uniformly on the vertical surface of the mold. Gravity would direct or shift the powder away from the vertical surface and towards the horizontal surface, before the molding process can be initiated. This particle shifting would prevent the formation of a seamless filter medium having a horizontal and a vertical surface. Even if metallic powder could be deposited in a mold with a nonplanar surface, the resulting filter medium would likely have a non-uniform structure. Gravity would direct or shift the air-laid metallic powder from higher portions of the mold towards lower portions of the mold, thereby resulting in a filter medium having some portions thicker than others. Accordingly, forming a high quality, non-planar, porous metallic filter medium with a conventional air-laying process would be extremely difficult, if not impossible. Third, conventional air-laying processes are inconvenient. For example, if a large filter medium is desired, then the metallic powder must be deposited from high above a mold. The increased height would require a larger manufacturing facility and consequently higher maintenance costs.

15

Summary of the Invention

In accordance with one aspect of the invention, a method of forming a porous medium comprises applying pressure to a first portion of a medium precursor including inorganic particles, separately applying pressure to a second portion of the medium precursor, and sinter bonding the inorganic particles together.

20

In accordance with another aspect of the invention, a porous medium comprises a first portion having a first axial dimension and a second portion having a second axial dimension. The second axial is greater than the first axial dimension and the first and

second portions each have a predetermined porosity.

In accordance with another aspect of the invention, a porous medium comprises a porous sintered inorganic body portion having a first end and a porous sintered inorganic end portion closing the end of the body portion, the porous body portion and the porous
5 end portion comprising a unitary structure.

In accordance with another aspect of the invention, a porous element comprises a porous medium of sintered inorganic particles and a porous substrate. At least a portion of the sintered inorganic particles are disposed within pores of the porous substrate, mechanically interlocking the porous medium and the porous substrate.

10 In accordance with another aspect of the invention, a process for making a porous element comprises contacting a porous substrate with a slurry including a liquid medium and inorganic particles and sintering the inorganic particles together within pores of the porous substrate to mechanically interlock the sintered inorganic particles to the porous substrate.

15 In accordance with another aspect of the invention, a porous medium comprises a porous sintered inorganic structure derived from a pressed mixture including a liquid medium and a plurality of inorganic particles having a nominal first size.

In accordance with another aspect of the invention, a method comprises applying pressure to a slurry including a liquid medium and inorganic particles and separating a
20 least some of the liquid medium from the slurry in response to the pressure.

In accordance with another aspect of the invention, a porous medium comprises a mass of sintered inorganic particles having a porosity of greater than about 50%.

In accordance with another aspect of the invention, a method comprises a mixture including a least a liquid medium, a plurality of inorganic particles having a nominal first size and a plurality of inorganic particles having a nominal size, the first size being less than the second size, and sinter bonding the plurality of inorganic particles having a
5 nominal first size and a plurality of inorganic particles having a nominal second size together.

In accordance with another aspect of the invention, a porous medium comprises a first plurality of inorganic regions having a first nominal size, a second plurality of inorganic regions having a second nominal size, wherein the first nominal size is less than
10 the second nominal size and the plurality of inorganic regions interspersed between the second plurality of inorganic regions. The porous medium further comprises a plurality of bonds interposed between the first plurality of inorganic regions and the second plurality of inorganic regions.

In accordance with another aspect of the invention, a mold apparatus comprises a
15 mold cavity arranged to contain a slurry and at least first and second dies. The first die is arranged to press a first portion of the slurry in the mold cavity and the second die is arranged to separately press a second portion of the slurry in the mold cavity.

These and other embodiments of the invention provide for a number of advantages. First, unlike conventional porous inorganic filter media, the porous inorganic filter media
20 according to various embodiments of the invention exhibit improved particulate retention and higher voids volumes. For example, a small, highly porous, filter medium embodying the invention can permit the same amount of fluid flow as a larger filter medium having a low porosity, while having substantially the same particulate retention

properties as the larger filter medium. A smaller filter medium uses less inorganic material than a larger filter medium, and can be used with a smaller housing which can also have less inorganic material. The use of less inorganic material in the filter medium and the housing reduces the likelihood that the inorganic filter medium will exhibit particle shedding or outgassing. Second, unlike conventional air-laying methods, methods according to various embodiments of the invention can produce inorganic filter media with high voids volumes and/or improved particulate retention properties without the difficulties of air-laying inorganic powders. Further, methods according to various embodiments of the invention can produce a high-quality filter medium having any desired shape.

Brief Description of the Drawings

Figure 1(a) is a schematic illustration of an embodiment of a process of the invention.

Figure 1(b) is a top view of a hat-shaped filter medium.

Figure 2 shows an example of a mold apparatus.

Detailed Description

One embodiment of the invention is directed to a process for making an inorganic filter medium, and in particular, a porous metallic filter medium. In one exemplary process, a slurry is formed. The slurry can include a liquid medium, inorganic particles, and an optional binder. In some embodiments, the inorganic particles include a plurality of inorganic particles having a nominal first size and a plurality of inorganic particles having a nominal second size, where the first size is less than the second size. Once

formed, the slurry can be processed in any suitable manner. Preferably, at least some of the liquid medium can be separated from the slurry before, during or after the slurry is processed, thus forming a green structure. Later, the inorganic particles in the green structure or slurry can bond together to form a porous inorganic filter medium. For
5 example, the green structure can be sintered in a furnace. The sintering can induce bonding between adjacent inorganic particles and can vaporize the liquid medium and/or binder in the green structure or slurry.

The slurry can include inorganic particles including any suitable metal-based material, ceramic material, or combination thereof which are sinterable. Examples of
10 metallic materials include metal-based compounds such as pure metals, metal alloys, dispersion strengthened metals, and combinations thereof. Specific, non-limiting examples of metallic materials include nickel, chromium, copper, tungsten, zinc, gold, silver, platinum, nickel alloys, Inconel, Monel, Hastelloy, stainless steel, and combinations and/or oxides thereof. Of these materials, nickel and stainless steel based materials are
15 preferred. In particular, nickel and stainless steel-based particles are highly resistant to corrosion and exhibit high strength. Exemplary ceramic materials include borides, oxides, and nitrides, such as BN, SiN, alumina, titania, etc. Further, any suitable combination of ceramic and/or metallic particles may be used. The particles may be made in any manner, including water or gas atomized metal powders, shattered metals, drawn or cast fibers,
20 sol-gel process ceramic powders, or flame sprayed powders.

The inorganic particles used to form the porous inorganic filter medium can be in any suitable form, including for example, powder or fiber. The inorganic particles can include non-uniformly shaped particles including dendritic, acicular, irregular or

fragmented particles. Alternatively, the inorganic particles can include uniformly shaped particles, such as spherical particles. Preferably, however, the inorganic particles have a shape which exhibits a high surface area. For example, micron-sized dendritic inorganic particles can exhibit a high surface area. Whether or not dendritic particles are used, the

5 inorganic particles may have a surface area in the range from about $0.01 \text{ m}^2/\text{g}$ to about $10 \text{ m}^2/\text{g}$ and preferably have a surface area greater than about $0.25 \text{ m}^2/\text{g}$. More preferably, the inorganic particles have a surface area between about $0.3 \text{ m}^2/\text{g}$ or less to about $3.0 \text{ m}^2/\text{g}$ or more. Suitable inorganic particles which can be used to form a porous inorganic filter medium include INCO '255 and INCO '210 nickel-based particles available from

10 Inco, Inc. INCO '255 particles have a nominal size of about 2.5 microns and a BET surface area of about $0.62 \text{ m}^2/\text{g}$. INCO '210 particles have a nominal size of about 0.7 microns and a BET surface area of about $2.0 \text{ m}^2/\text{g}$.

Using inorganic particles with a high surface area can provide for a number of advantages. First, lower sintering temperatures can be used when sintering inorganic

15 particles having a high surface area together. For example, high surface area dendritic particles typically have a plurality of appendages or tree branch-like structures. Because of these appendages, a mass of dendritic particles can have more points of contact and therefore more potential bonds between adjacent particles than a mass of relatively low surface area particles (e.g., spherical particles). As a result of this increased number of

20 bonds, a mass of low-temperature sintered, high surface area, dendritic inorganic particles can have substantially the same structural stability as a mass of high-temperature sintered, low surface area, inorganic particles.

Advantageously, lower sintering temperatures can result in lower production costs.

Low temperature sintering processes consume less energy than high temperature sintering processes and can be performed in less expensive sintering apparatuses. For example, a porous inorganic filter medium can be formed by sintering high surface area inorganic particles together at relatively low temperatures in a relatively low-cost, stainless steel sintering apparatus. On the other hand, a porous inorganic filter medium formed by sintering low surface area inorganic particulates together may require the use of a relatively high-cost, high-temperature ceramic sintering apparatus. Also, an inorganic filter medium made from high surface area inorganic particles can have improved particulate retention properties. For example, the paths through the pores in a filter medium formed from sintered, high surface area, inorganic particulates such as dendritic particulates can be highly tortuous and winding. These tortuous and winding pore paths in the filter medium can form traps, trapping or sieving any particulate contaminants which might otherwise pass therethrough. The tree branch-like appendages of dendritic inorganic particles may not only define irregularly shaped pores in the porous inorganic filter medium to be formed, but may also extend into the pores without contacting an appendage of an adjacent dendritic inorganic particle. The appendages which extend into the pores can obstruct contaminants which may otherwise pass through pores not having any appendages therein.

The inorganic particles can also have any size suitable for forming an inorganic filter medium. Smaller size inorganic particles yield a porous medium that has enhanced retention characteristics but may also have higher differential pressures. For example, the inorganic particles can have a nominal size between about 0.05 micron to about 200

microns, or between about 1 to about 40 microns. The inorganic particles used to form the filter medium may have only a single nominal particles size or may comprise a mixture (e.g., a generally or substantially uniform mixture) of nominal particle sized, such as a mixture of a plurality of inorganic particles having a nominal first size and a plurality of
5 inorganic particles having a nominal second size, where the first size is less than the second size. For many embodiments, a significant portion of the filter medium, such as the entire filter medium, includes a generally or substantially uniform mixture of inorganic particles having at least two different nominal sizes. Put another way, the inorganic particles having at least two different nominal sizes may be substantially uniformly
10 distributed amongst each other in the filter medium, preferably throughout the filter medium. Of course, the inorganic particles used to form the porous inorganic filter medium can include three, four, five, etc. groups of inorganic particles having different nominal sizes. Regardless of the specific number of different groups of particles used, the different groups of particles are preferably mixed together. When the inorganic particles
15 having at least two different nominal sizes are mixed and then sintered together, distinct inorganic regions and bonding regions can form in the resulting filter medium. For example, plural inorganic particles having first and second nominal sizes can be mixed, and then sintered. The resulting porous inorganic filter medium can have a plurality of first and second inorganic regions (respectively corresponding to the plural inorganic
20 particles having first and second nominal sizes), and a plurality of sinter-bonds interspersed between the plurality of first and second inorganic regions. The first and second plurality of inorganic regions can be distinct from the plurality of sinter-bonds which can result from solid or liquid state diffusion between the portions of contacting

inorganic particles.

The plurality of inorganic particles having a nominal first size and the plurality of inorganic particles having a nominal second size can be used in any suitable proportion and can have a variety of characteristics. The slurry can include (e.g., based on the total weight of the slurry or the total weight of the inorganic particles in the slurry) from about 2-98 wt. %, preferably about 30-50 wt. %, e.g., 40 wt. %, inorganic particles having a nominal first size, and from about 2-98 wt. %, preferably about 50-70 wt. %, e.g., 60 wt. %, inorganic particles having a nominal second size, where the nominal first size is preferably less than the nominal second size. For example, the inorganic particles having a nominal first size can be from about 0.001 micron to about 0.99 microns, while the inorganic particles having a nominal second size can be from about 0.5 micron to about 45 microns. For example, the first size may be about 0.7 micron, while the second size can be about 2.5 microns. In a preferred embodiment, the plurality of inorganic particles having a nominal first size and/or the plurality of inorganic particles having a nominal second size include high surface area inorganic particles. In many embodiments the largest nominal particle size is preferably no greater than about 10 times the smallest nominal particle size, more preferably no greater than about 6 times, even more preferably no greater than about 4 or 2 times the smallest nominal particle size. The plurality of inorganic particles having a nominal first size (e.g., 0.7 micron) can have a BET surface area of about 2.0 m²/g and the inorganic particles having a nominal second size (e.g., 2.5 micron) can have a BET surface area of about 0.62 m²/g. Furthermore, the plurality of inorganic particles having a nominal first size and a plurality of inorganic particles having a nominal second size may be made of the same or different material. For example, the

inorganic particles having a nominal first size can include an inorganic material having a low melting point such as nickel, while the inorganic particles having a nominal second size can include an inorganic high melting point material (e.g., stainless steel).

Porous inorganic filter media derived from inorganic particles having at least two
5 different nominal sizes, or having plural first and second inorganic regions having different nominal sizes can provide for a number of advantages. For example, a porous inorganic filter medium made from inorganic particles having at least two different nominal sizes can have increased ductility and/or exhibit a reduced pressure differential. A porous inorganic filter medium with increased ductility is less likely to break or crack
10 when subjected to pressure. Moreover, porous inorganic filter media made from particles having at least two different nominal sizes can result in a porous inorganic filter medium having an increased surface area and thus improved particulate retention properties. For example, if an inorganic filter medium is made from a plurality of inorganic particles having a small size (e.g., 0.7 microns) and a plurality of inorganic particles having a
15 larger size (e.g., 2.5 microns), the larger size inorganic particles can define large pores in the filter medium. The smaller size particles, which can be bonded to one another, and the larger size inorganic particles, can occupy the space defined between the larger particles thereby forming even smaller pores and more tortuous pore paths than the larger particles alone would form. As a result, a fluid such as a gas can flow through the smaller
20 pores which are provided by the larger and smaller particles and the more tortuous pore paths. However, particulate contaminants, which may have passed through the larger pores, can be retained by the smaller pores disposed between the larger and smaller particles. Preferably, the plurality of inorganic particles having a nominal first size and

the plurality of inorganic particles having a nominal second size include high surface area inorganic particles such as dendritic particles. As explained above, high surface area inorganic particles such as dendritic particles can increase the internal surface area and the particulate retention properties of a resulting porous inorganic filter medium.

5 The slurry can include any suitable binder. Preferably, the binder can stabilize or bind the inorganic particles in the slurry so that the inorganic particles do not substantially settle in the slurry. For example, for many slurries 3-8 grams of binder per liter of liquid medium may be sufficient. The binder can include any suitable synthetic or natural polymer. Exemplary binders include carboxymethylcellulose, carboxyethylcellulose, guar
10 gum, alginates, methylcellulose, and locust bean gum. Particularly preferred binders include polyacrylic acids, such as Carbopol 941 and 934 (available from B.F. Goodrich Chemicals Company under the trade name Carbopol). Advantageously, the binder in the slurry can help reduce the likelihood of any unintended shifting of inorganic particles in the slurry, thereby decreasing the likelihood that the resulting inorganic filter medium will
15 have a non-uniform pore structure.

 The slurry can also include any suitable liquid medium. Preferably, the liquid medium has a lower viscosity than the binder, and together with the binder imparts a predetermined viscosity to the slurry. The viscosity of the slurry may be determined empirically such that the viscosity is low enough that the liquid medium separates
20 sufficiently from the slurry when the slurry is pressed and the viscosity is high enough that particles remain uniformly suspended in the slurry until the slurry is pressed. The viscosity of the slurry can be adjusted by the addition of more or less liquid medium and/or binder, and can depend upon such factors as the size of the particles and the

technique used to process the slurry. For example, a slurry which is to be coated can have a different viscosity than a slurry which is to be pressed in a mold or extruded. Examples of suitable liquid media include semisolid materials such as waxes and less viscous materials such as methanol, isopropyl alcohol, water or any combination of these substances. In one embodiment, the liquid medium can have a high surface tension (e.g., water). However, if a high surface tension liquid medium is used in the slurry, the liquid medium is preferably removed from the slurry or the green structure slowly to reduce the likelihood of cracking the subsequently formed green structure. For example, if the slurry includes water as a liquid medium, the slurry can be dried, e.g., by placing the slurry in a low temperature oven for a period of time to remove the water from the slurry and form a green structure.

Preferably, the liquid medium has a low surface tension. For example, the liquid medium can include a liquid having a surface tension less than water, or a surface tension less than about 72.4 dynes per centimeter. Non-limiting examples of liquid media having a surface tension less than about 72.4 dynes per centimeter include methanol, ethanol, hexane, benzene, and low surface tension aqueous solutions. Advantageously, the use of a low surface tension liquid medium in the slurry can reduce the likelihood of potential cracking that may occur if the liquid medium is removed from the slurry (e.g., to form a green structure). For example, some or substantially all of the liquid medium can be removed from the slurry by compressing the slurry. The low surface tension liquid medium can separate cleanly from the compressed slurry without substantially disrupting the contact between adjacent inorganic particles. Low surface tension liquids typically flow more easily than high surface tension liquids, because they do not have a tendency to

pull upon themselves. The tendency of a high surface tension liquid medium to pull upon itself can potentially cause a subsequently formed green structure to crack if the high surface tension liquid medium is removed from the slurry or the green structure too quickly.

5 In a particularly preferred embodiment of the invention, the slurry can include a spacing agent. Spacing agents can help form pores in the green structure or final product and can reduce the likelihood that the inorganic particles may collapse during subsequent processing (e.g., during the removal of the liquid medium or sintering). Exemplary spacing agents include oxamide, methylcellulose, ammonium salts of carbonic acid or
10 other weak organic acids, such as formic, acetic, or oxalic acids, and salts such as calcium chloride. Spacing agents in the slurry and/or the later formed green structure can be removed from the green structure before, after, and/or during the sintering of the green structure. Removal of the spacing agent can occur in any number of ways including decomposing the spacing agent by combustion, sublimation or leaching (e.g., chemical or
15 physical leaching).

The use of spacing agents in embodiments of the invention can result in a porous inorganic filter medium having improved strength and/or a greater voids volume. For example, when spacing agents are incorporated into the slurry, the slurry and subsequently formed green structure can be compressed without significantly decreasing the voids
20 volume of the resulting inorganic filter medium. Compressing the slurry can favorably increase the contact points and potential bonds between adjacent inorganic particles without inadvertently collapsing the internal pore structure of the resulting porous inorganic filter medium. If the internal pore structure collapses during processing, the

resulting porous inorganic filter medium may have a reduced voids volume. When the spacing agents are removed from a compressed green structure or slurry, pores can be left in their place. By using spacing agents in the slurry, a voids volume or porosity of greater than about 50%, preferably greater than about 70% or about 75%, and more preferably greater than about 80% or about 90% can be achieved. Most preferably, the voids volume or porosity is in the range from about 60% to about 80%, e.g., about 70%.

In an illustrative example, a highly porous inorganic medium can be formed with spacing agents. A slurry including inorganic particles, a binder, a liquid medium and a spacing agent, can be agitated to uniformly disperse the slurry components. The slurry can then be processed (e.g., by coating, extruding, or molding) and may then be compressed. Compressing the slurry forces the inorganic particles in the slurry together and separates some of the liquid medium from the slurry. After a portion of the liquid medium is removed from the slurry, a green structure is formed. The green structure can be heated to a suitable temperature range to decompose the spacing agent into, e.g., a gas. The gas then separates from the green structure leaving pores where the spacing agents were before they were decomposed. A highly porous green structure is subsequently produced, and can be sintered to produce a highly porous inorganic filter medium.

Alternatively, instead of removing the spacing agent in a separate process, the spacing agent can be removed during or after the sintering process. For example, a green structure having spacing agents and inorganic particles can be placed in a sintering furnace. The green structure can then be heated to decompose the spacing agents while sintering the inorganic particles together. The spacing agent in the slurry and/or the green structure can help maintain constant spacing between the inorganic particles when

compressing, heating and/or sintering the slurry or green structure. Consequently, the likelihood that the inorganic particles may collapse when compressing and/or sintering a porous inorganic filter medium precursor (e.g., a slurry or green structure) is reduced, thereby resulting in highly porous inorganic filter medium.

5 The slurry can optionally include additives. Additives can include one or more of sinter aids, viscosity reducing agents, viscosity increasing agents, fillers, lubricants, surfactants, etc. For example a surfactant available under the trade designation Triton X may be used.

10 The slurry can be agitated or mixed in any suitable manner and with any suitable apparatus. For example, the slurry can be mixed in a blender, or by a stirrer or a shaker. Preferably, the slurry can be agitated or mixed so that the inorganic particles in the slurry are uniformly dispersed. By doing so, the inorganic particles in the slurry, green structure or a subsequently formed porous inorganic filter medium will also be substantially uniformly distributed throughout the green structure of filter medium. The uniform
15 distribution of inorganic particles in a filter medium also provides for a substantially uniform distribution of pores (i.e., uniform porosity) to the filter medium.

20 The slurry can be processed in any suitable manner. Exemplary shaping methods include pressing, coating, molding, and extrusion. Exemplary pressing methods include cold pressing, hot pressing, and isostatic pressing. Pressing the slurry can be advantageous. For example, pressing the slurry prior to sintering can compact the inorganic particles together and can increase contact and potential bonds between adjacent inorganic particles. As explained previously, increasing the bonds between adjacent inorganic particles can increase the strength of the resulting porous inorganic filter

medium. The slurry can also be coated. Exemplary coating methods include doctor blade coating, roller coating, curtain coating, dip coating, slip coating etc. For example, a substantially planar surface of a porous or nonporous structure can be coated with a layer of slurry. The substantially planar layer of slurry can then be further processed (e.g.,

5 compressed, sintered) to form a substantially planar porous inorganic filter medium. The inorganic particle-containing slurry can also be molded into any desired shape.

Exemplary molding processes include cast molding or injection molding. For example, the slurry can be injection molded into a mold defined by cup-shaped dies to form a cup shaped slurry. The cup shaped slurry can then be processed (e.g., pressed, heated, and/or

10 sintered) to form a cup shaped porous inorganic filter medium. The slurry can also be extruded into any desired shape. For example, the inorganic particle containing slurry can be extruded through a die (e.g., substantially annularly shaped) into the shape of a seamless tube. The seamless tube-shaped slurry can then be further processed into a seamless, tube-shaped, porous, inorganic filter medium. Finally, any combination

15 methods can be used to shape or process the slurry. For example, the slurry may be deposited or coated on an inner portion of a female mold. Thereafter, a male mold can compress the slurry to further shape the slurry into a desired structure. The compressed slurry can then be processed (e.g., by sintering) into a porous inorganic filter medium.

In one preferred embodiment, a filter medium such as a non-planar filter medium
20 can be produced by separately pressing individual portions of a filter medium precursor (e.g., a slurry or green structure) such as a non-planar precursor with, e.g., two or more dies, to provide predetermined characteristics such as porosities, e.g., uniform porosities, in different portions of the precursor, including portions having different axial dimensions.

The dies can cooperate to define the molded shape produced by a molding apparatus.

Preferably, the two or more dies of the molding apparatus can move in the same or opposing directions or planes along a common axis to press the filter medium precursor.

The pressure applied, the pressing time, and/or the distance traveled by one or more dies

5 to compress a portion of a filter medium precursor may be the same or different than that of other dies compressing other portions of the filter medium precursor. For example, the pressure applied, pressing time, and/or distance traveled by one or more dies used to compress a first portion of a filter medium precursor can be less than that of one or more other dies compressing a second portion of the filter medium precursor. This can be

10 preferable if the first portion has a shorter axial dimension in the pressing direction and/or a smaller volume of inorganic particles than the second portion. By doing so, the longer second portion can be compressed to have any suitable predetermined characteristic, e.g., particle density or distribution or porosity which is the same as or different from the shorter first portion, even though the second portion has a different axial dimension in the
15 direction of pressing and/or a greater volume of inorganic particles than the first portion.

The characteristics of the separate portions of the medium may be predetermined in accordance with a compression ratio for each portion. The compression ratio for each portion is the ratio of the desired final axial dimension of the portion to the sum of the desired final axial dimension and the stroke or axial displacement of the die(s) as it (they)

20 compress the portion of the medium precursor. For example, if the predetermined characteristic of the porous medium is uniform porosity for all portions, then each portion may be compressed at the same compression ratio.

The application of pressure to individual portions of the filter medium precursor removes many limitations that may be present when pressing a shaped filter medium precursor with a single, unidirectional rigid die having a predetermined complex shape. For example, if a single, unidirectional rigid die (not shown) is used to press one side

5 (e.g., the side including a concave surface) of the cup- or hat-shaped precursor 21 shown in Figure 1(a), the distance over which the rigid die can travel can be limited by the distance over which the rigid die travels to compress the shorter first portion 21(a) or the third portion 21(c) of the hat-shaped precursor 21, and not the longer second portion 21(b). The compressed first and/or third portions 21(a), 21(c) can prevent further

10 movement of the rigid die before the rigid die can fully compress the second portion 21(b).

In contrast, in embodiments of the invention, substantially all portions of a filter medium precursor can be substantially fully compressed, providing, for example, substantial uniformity of the distribution and/or density of the inorganic particles or the

15 porosity in substantially all portions of the precursor and the resulting porous inorganic filter medium. A porous inorganic filter medium having a uniform distribution and/or density of inorganic particles can have a uniform porosity.

One example of a process for forming a porous inorganic filter medium using two or more dies is shown in Figure 1(a). Figure 1(a) is a schematic diagram of an example of

20 a process for pressing a hat-shaped filter medium precursor 21, which can later processed (e.g., sintered) to form a hat-shaped porous inorganic filter medium. Figure 1(b) shows a top view of the hat-shaped filter medium precursor 21 shown in Figure 1(a). The hat-shaped filter medium precursor can be characterized as having three portions including a

first portion 21(a), second portion 21(b), and a third portion 21(c). The first portion 21(a) can form the brim of the hat shape, while an annularly shaped second portion 21(b) and a disk-like third portion 21(c) can collectively form the crown of the hat shape. Pressure can be applied to the precursor 21 by one or more dies 31(a), 31(b), 32(a), 32(b), 33(a), 5 33(b), which can correspond to movable or non-movable dies of molding apparatus.

Although Figure 1(a) shows dies on opposing sides of the precursor 21, in other embodiments, pressure can be applied to only one face of a precursor portion. For example, pressure can be applied to the precursor 21 with select dies 31(a), 32(b), 33(b), while one or more corresponding dies 31(b), 32(a), 33(a) on the opposing side of the 10 precursor 21 are either stationary or retractable.

In this exemplary process, a slurry including substantially uniformly distributed inorganic particles can be introduced into a mold cavity. One or both of the dies 31(a), 31(b) can move and apply pressure to one or both opposing surfaces of the first portion 21(a) to compress the first portion 21(a). As the slurry is pressed by the dies, the liquid 15 medium may be squeezed out of the slurry through gaps between the dies and/or between the dies and the housing, the size of the gaps may vary depending on factors such as the size of the particles in the slurry. Smaller gaps may be provided for smaller particles. For many embodiments the gaps may be in the range from about 0.001 inch to about 0.004 inch. Before, during or after the application of pressure to the first portion 21(a), 20 pressure can be applied to one or both opposing sides of the second portion 21(b) and/or the third portion 21(c) of the filter medium precursor 21 with one or more dies 32(a), 32(b), 33(a), 33(c). Any or all of the dies 32(a), 32(b), 33(a), 33(c) can operate separately or independently of each other and separately or independently of either or both of the dies

31(a), 31(b) applying pressure to the first portion 21(a). Preferably, all dies end their stroke at the same time.

By separately pressing individual filter medium precursor portions, such as the first portion 21(a), second portion 21(b), and the third portion 21(c) of the precursor 21 shown in Figure 1(a), the compression of each individual portion of the filter medium precursor (e.g., a slurry) can be maximized or tailored to predetermined specifications. This may be advantageous if the porous inorganic filter medium to be formed has a non-planar shape and a substantially uniform porosity. The individual portions may then be compressed at the same compression ratio. For example, in Figure 1(a) the dimension D_2 of second portion 21(b) in the direction of pressing is greater than the dimension D_1 of the first portion 21(a) and the dimension D_3 of the third portion 21(c) in the direction of pressing. To compress the longer second portion 21(b) to substantially the same particle density as the shorter first and second portions 21(a), 21(c), the pressure applied, the pressing time, and/or the distance traveled by one or both of the dies 32(a), 32(b) applying pressure to the second portion 21(b) can be greater than that of the dies 31(a), 31(b), 33(a), 33(b) applying pressure to the first or third portions. In contrast, if a single unidirectional die is used to simultaneously apply pressure to one side (e.g., the concave side) of the filter medium precursor 21, the compression of the second portion 21(b) may not be maximized, because the distance over which the single unidirectional die can travel may be limited to the distance over which the first and/or third portions 21(a), 21(c) can be compressed. Accordingly, in embodiments of the invention, characteristics such as the distribution and/or density of inorganic particles and/or the porosity in substantially all portions of a filter medium precursor (even the portions having long dimensions in the direction of

pressing), and the subsequently formed porous inorganic filter medium, can be predetermined, for example, can be substantially the same, thus providing the resulting porous inorganic filter medium with a uniform particle and pore distribution, or different, thus providing a filter medium with different portions having different characteristics.

- 5 Further, the method and apparatuses according to embodiments of the invention can be used to mass produce high quality porous inorganic filter media to close tolerances.

One example of a mold apparatus embodying the invention is shown in Figure 2.

A hat-shaped filter medium precursor 21 is formed by depositing a slurry in a mold cavity and pressing the slurry with several dies. The first portion of the precursor is pressed by
10 a first die 5 and the third portion of the precursor is pressed by another die 8. The second portion of the precursor is pressed between two moving dies 6 and 4. Gaps between the dies and between the dies and the housing 2, 3 provide for discharge of the liquid medium from the slurry. The dies are connected to driving mechanisms, such as pistons, to effect movement of the dies along a common axis A.

- 15 Nonplaner porous media having a variety of desired shapes may thus be formed as a unitary structure, i.e., a structure having no bonds, e.g., welds, braze bonds, adhesive bonds, etc., between various components of the filter medium. For example, the hat-shaped medium precursor includes a second body portion and a third end portion which closes the end of the body portion, and the body portion and the end portion comprise a
20 unitary structure free of any bonds. While the illustrated body portion is generally cylindrical or slightly conical, it may have a variety of suitable cross sectional shapes and yet may be conveniently closed at one end by an end portion which forms a unitary structure with the body portion. The second body portion and the first brim portion of the

hat-shaped precursor may also comprise a unitary structure free of any bonds.

If desired, some of the liquid medium can be removed from the slurry or green structure. Preferably, a substantial portion of the liquid medium is removed from the slurry or green structure. Removal of the liquid medium can occur in any suitable
5 manner. For example, the liquid medium can be removed from the slurry by drying, vacuum, centrifuging, compression of the slurry, or any combination of suitable liquid removal methods. In one embodiment, the liquid medium can be removed from the slurry by evaporating the liquid medium from the slurry to form a green structure. For example, the slurry can be heated to a temperature between about 100° C to about 450° C to
10 evaporate the liquid medium from the slurry. Once a substantial portion of the liquid medium is removed from the slurry, a freestanding green structure having inorganic particulates can be produced. The freestanding green structure can then be handled for further processing. For example, the green structure can be transferred to a sintering device for sintering.

15 In a preferred embodiment, the slurry can be compressed to separate the liquid medium from the slurry. The slurry can be compressed by cold, hot or warm pressing. Compressing the slurry can not only facilitate removal of the liquid medium from the slurry, but can also increase the contact and potential bonds between adjacent inorganic particles. In a preferred embodiment, a fine porous structure such as a mesh, woven
20 fabric or a nonwoven fabric can be used to help separate the liquid medium from the slurry. For example, a fine pore mesh can lie adjacent to a slurry. Pressure can be applied to the fine pore mesh and the slurry so that the liquid medium separates from the slurry by passing through the pores of the mesh while the mesh retains the binder and the

inorganic particles. Preferably, the liquid medium passing through the fine porous structure is substantially pure.

If more structural stability in the green structure is desired, then more liquid medium can be removed from the slurry and/or the subsequently formed green structure.

- 5 A green structure with added structural stability is preferred if the porous inorganic filter medium to be produced is to have a precisely defined shape, such as a cup shape.

Removal of additional liquid medium from the green structure can occur in any suitable manner and can use any suitable combination of liquid medium removal methods. For example, after compressing a substantial portion of the liquid medium from the slurry,

- 10 even more liquid medium can be removed from the slurry by heating the compressed slurry in a low temperature-heating device. Heat from the heating device can remove (e.g., by evaporation) additional liquid medium from the squeezed slurry. Alternatively or additionally, the green structure may be further compressed to separate additional liquid medium from the green structure. As more liquid medium is removed from the slurry or
15 green structure, the structural stability of the green structure can be increased.

- Once a green structure is formed from the slurry, the inorganic particles in the green structure can then be bound together. The inorganic particles can be bound by sintering the inorganic particles together. Sintering can occur in any suitable device or atmosphere. Exemplary sintering devices include ceramic and stainless steel sintering
20 apparatuses (e.g., ovens). Preferably, the sintering atmosphere includes an inert or a reducing atmosphere. Reducing or inert sintering atmospheres can prevent or inhibit the formation of oxides on the inorganic particles. Exemplary inert atmospheres include argon, vacuum, helium, nitrogen, or mixtures thereof. Exemplary reducing atmospheres

include hydrogen, carbon monoxide, dissociated ammonia, and mixtures thereof.

The sintering temperature can include any suitable temperature, but is preferably high enough to induce solid or liquid state diffusion of atoms between adjacent inorganic particles to form bonding regions (e.g., sinter-bonds). Typical sintering temperatures can
5 be between about 450 ° C to about 900 ° C. The sintering temperature can vary depending upon the type of inorganic particles used. For example, typical sintering temperatures for nickel-based particles can be between about 500° C and about 750° C, and preferably between about 525° C and about 650° C. On the other hand, typical sintering temperatures for stainless-steel based particles can be somewhat higher e.g.,
10 between 1050°C and 1150°, because stainless steel has a higher melting point than nickel.

After the inorganic particles bond together (e.g., by sintering), the formed porous inorganic structure can be subjected to any suitable post-bonding operation. Post-bonding operations can include working treatments such as pressing or rolling; heating treatments such as annealing or re-sintering; and/or finishing treatments such as surface treating (e.g.,
15 plating). Such post-bonding operations can be desirable if a porous inorganic structure having particular properties is desired. For example, the porous inorganic structure can be annealed to reduce any internal stress that can be present therein.

The porous inorganic filter medium can have any suitable characteristics. For example, the porous inorganic filter medium can be highly porous, strong, ductile, and
20 can have favorable particle retention properties. The porous inorganic filter medium can also have a high surface area and/or irregularly shaped pores (e.g., dendritically shaped pores). For example, in embodiments of the invention, the inorganic filter medium can include a BET surface area of at least about 0.25 m²/g. Preferably, the inorganic filter

medium can include a BET surface area of at least about $0.35 \text{ m}^2/\text{g}$.

The resulting porous inorganic filter medium can have any suitable voids volume or porosity and pore rating (pore size), preferably a high voids volume and a small pore size. The porous inorganic filter medium preferably can have a voids volume of at least
5 about 50%. More preferably, the porous inorganic filter medium can include a voids volume of at least about 70% or about 75%, or even at least about 80% or about 90% or more. Preferably the voids volume or porosity is in the range from about 60% to about 80%, e.g., 70%. The porous inorganic filter media embodying the invention can have pore sizes and/or characteristics suitable for use in a wide variety of processes, including
10 microfiltration, ultrafiltration, and/or nanofiltration processes. For example, some porous inorganic filter media can have a nominal pore size of about 10 microns or more, in the range from about 1 micron to about 10 microns, in the range from about 0.04 micron to about 10 microns, or in the range from about 0.01 micron or less to about 1 micron. Other porous inorganic filter media embodying the invention can have the nominal pore
15 dimensions in the range from about 10 angstroms or less to about 200 angstroms or more. Yet other porous inorganic filter media embodying the invention can have a molecular weight cutoff rating of about 200 daltons or less, in the range from about 200 daltons to about 1000 daltons, in the range from about 1000 daltons to about 500,000 daltons, or greater than about 500,000 daltons. In some processes (e.g., ultrafiltration), the porous
20 inorganic filter medium can have an absolute removal rating within the range from about $0.04 \text{ }\mu\text{m}$ to about $20 \text{ }\mu\text{m}$.

The porous inorganic filter media can also have pores extending from surface to surface in a relatively uniform structure, or in a tapered or graded pore structure. A

porous inorganic filter medium having a tapered or graded structure can be formed by any suitable method. For example, two green inorganic structures with different voids volumes and/or pore ratings may be placed together and sintered. The inorganic particles within each of the green inorganic structures can bond together, while the two green

5 inorganic structures can bond to each other. In another example, a porous inorganic filter medium with a first pore rating or a green structure capable of producing a porous inorganic filter medium with the first pore rating can be coated with an inorganic-particle containing slurry capable of forming a porous inorganic filter medium with a second pore rating. This coated structure can then be processed (e.g., sintering) into a single porous

10 inorganic filter medium with a first pore rating and a second pore rating. In yet another example, two separately formed porous inorganic filter media with two different pore ratings can be placed adjacent to one another and joined (e.g., by sintering or welding). A porous inorganic filter medium having a graded or a tapered pore structure can provide for a number of advantages. For example, the portion of the porous inorganic filter medium

15 having a larger pore rating can serve as a prefilter or support structure for the porous inorganic filter medium having a smaller pore rating. Prefilters can increase the useful life of a filter medium, by preventing macroscopic particles in a fluid stream from prematurely fouling or clogging a downstream portion of a filter medium.

The porous inorganic filter medium can have any suitable shape. The porous

20 inorganic filter medium can planar or curved, and more specifically can be shaped as a disk, plate, cup, envelope, etc. In one embodiment, the filter medium can have a pleated structure. By providing an inorganic filter medium with a pleated structure, the filter area available for a limited envelope (e.g., one defined by a housing) can be increased. In a

preferred embodiment, the porous inorganic filter medium can comprise a thin planar structure, such as a membrane. Although the porous inorganic filter medium can have any suitable thickness (whether cup shaped, planar, etc.), it preferably has a thickness from about 0.01 to about 0.5 inch, or between about 0.1 to about 0.4 mm or more.

5 Advantageously, the porous inorganic filter media can exhibit reduced particle shedding and increased particulate retention properties. In accordance with embodiments of the invention, a smaller filter medium can be formed if the filter medium has a higher voids volume, because a smaller filter medium having a high voids volume can permit the same amount of fluid through as a larger filter medium having a low voids volume. A
10 smaller filter medium can require less inorganic material than a larger filter medium, and can be used with a smaller housing which also requires less material. The use of less inorganic material in a filter medium and the housing can reduce the likelihood that the inorganic filter medium will exhibit particle shedding or outgassing. Accordingly, the low particle shedding and/or low outgassing porous inorganic filter media embodiments of the
15 invention can be ideally suited for use in point of use filters where particle shedding and outgassing is preferably minimized.

 The porous inorganic filter medium can form part of a filter element. The filter element can also include a porous substrate, and can have any suitable shape or form. For example, the filter element can be planar, cylindrical, cup shaped, pleat-shaped, etc. The
20 substrate may or may not be bonded to the filter medium, and can provide functions such as support, drainage, and/or prefiltration capability to a filter medium. The porous substrate can also be located upstream and/or downstream of the porous inorganic filter medium. Suitable porous substrates can include PMM™ or PSS™ available from Pall

Corporation, Cortland, N.Y.

The porous substrate can have any suitable form. The shape of the porous substrate can be chosen according to the desired filter element to be formed. For instance, if a pleated filter element is desired, then a porous inorganic filter medium can be formed on, or concurrently with a pleated porous substrate. Alternatively, if a cylindrical filter element is desired, then the slurry can be deposited on a generally cylindrical porous substrate. Examples of porous substrates include screens, meshes, porous plates, and woven and nonwoven fabrics. The porous substrate can also include sintered inorganic particles or have a larger pore rating than the supported filter medium. Further, the substrate can have any suitable thickness such as a thickness of about 1/100 inch to about 1/10 inch.

The porous substrate can be made of any suitable material. The porous substrate can include any inorganic material, and can include the same or different material than the inorganic material used in the porous inorganic filter medium. For example, the porous substrate can include a metal such as stainless steel or a ceramic such as alumina, while the porous inorganic filter medium can include a metal such as nickel. Preferably, the porous substrate includes a material which does degrade when subjected to a high-temperature process (e.g., sintering).

The filter element can be formed in any suitable manner. In one method, a porous inorganic filter medium precursor can be joined to a porous substrate, prior to sintering. The porous inorganic filter medium precursor can be a slurry which can be coated onto or impregnated into the porous substrate (e.g., a stainless steel nonwoven fabric). If desired, the resulting structure can be shaped (e.g., corrugated). The slurry/porous substrate

combination can then be subjected to the previously described liquid medium removal and/or sintering processes. The sintering process not only sinters the inorganic particles in the slurry together, but can also optionally sinter the inorganic particles to the porous substrate. Alternatively, the porous inorganic filter medium precursor can be a green structure which can be separately formed, and then placed adjacent to a porous substrate. The combined green structure/porous substrate can be sintered to bond the inorganic particles in the green structure together while sintering the inorganic particles to the porous substrate. In another example, a porous inorganic filter medium precursor and a porous substrate precursor can be joined and processed together. For example, the porous inorganic filter medium precursor may be a slurry which can be coated on a porous substrate precursor, such as a green inorganic fabric mesh. The mesh-slurry combination can then be subjected to the previously described liquid medium removal and/or sintering processes to form a filter element. Alternatively, a green structure capable of forming a porous inorganic filter medium can be placed on a green inorganic fabric mesh and sintered. During sintering, the inorganic particles in both the green structure and the green inorganic fabric mesh can bond together, while the green structure and the green inorganic fabric can bond to each other. In yet another example, a porous inorganic filter medium can be joined to a porous substrate, while neither the porous inorganic filter medium nor the porous substrate is in the form of a precursor. For example, a porous substrate can then be joined to the porous inorganic filter medium by methods such as sintering, soldering or welding.

A filter element can be formed by coating a porous substrate with a slurry so that the slurry partially or fully impregnates pores of the porous substrate, especially the layer

or layers of pores just below the coated surface of the substrate. By partially or fully impregnating the pores of the porous substrate with the slurry including the inorganic particles, the resulting porous inorganic filter medium can be reliably joined to the porous substrate. For example, a thin layer of slurry can be coated (e.g., a slip coated) onto a

5 planar or cylindrical porous substrate so that at least some of the slurry including the inorganic particles impregnates the pores of the porous substrate near the surface. After impregnating the substrate with the slurry, the inorganic particles in the slurry can be sintered together. Preferably, the substrate has a higher sintering or melting temperature than the inorganic particles in the slurry. For example, the inorganic particles may

10 comprise nickel and the substrate may comprise a higher temperature material such as stainless steel. The impregnated substrate can be heated to a temperature sufficient to sinter the inorganic particles together, but not to the porous substrate. At the impregnated region of the resulting filter element, at least a portion of the porous inorganic filter medium and a portion of the porous substrate are mechanically engaged or interlocked at

15 the surface of the porous substrate by means of the sintered inorganic particles locked in the pores of the substrate. Preferably, the engagement or interlocking between the porous inorganic filter medium and the porous substrate can occur without substantial fusing or sintering between the porous substrate and the porous inorganic filter medium. Put

another way, the porous substrate and the porous inorganic filter medium can be joined

20 together without the presence of a substantial number of sinter bonds between the porous structure of the filter medium and the porous structure of the porous substrate.

The porous substrate can be impregnated with the slurry in any suitable manner. In some embodiments, the slurry can be coated onto the porous inorganic substrate in a

manner sufficient to partially or fully impregnate the porous substrate with the slurry. For example, a cylindrical or planar porous substrate can be coated with a layer of slurry by dip coating, roller coating, doctor blade coating, etc. The coated slurry layer may be somewhat thinner or wetter and a portion of the slurry including the particulates partially

5 impregnates a surface of the porous substrate. The slurry layer may be coated in a manner such that the resulting porous inorganic filter medium has a thickness of less than about 0.060 inch, preferably less than about 0.040 inch, or preferably less than 0.020 inch or 0.010 inch, e.g., about 1 to about 2 thousandths of an inch. The inorganic particles in the slurry at the impregnated region of the porous substrate can then be sintered together

10 within the pores at the surface of the porous substrate. The resulting filter element can include a porous inorganic filter medium in the form of a thin membrane on a porous substrate. At the impregnated region, the thin membrane and the porous substrate can be interlocked mechanically or engaged. If desired, an operation such as pressing (e.g., isostatic pressing or calendering) vacuum, pressure, or any suitable combination of such

15 operations can be used to help impregnate the pores of the porous substrate with the slurry. A filter element having a thin porous inorganic membrane at the surface of a porous substrate can be structurally stable, yet have a low pressure drop. In contrast, a porous inorganic depth filter may have a higher pressure drop.

Sintering the inorganic particles of the porous inorganic filter medium together

20 within the pores of the porous substrate, but not to the porous substrate can be advantageous. For example, the substantial absence of additional sinter bonds between the porous inorganic substrate and the filter medium can result in a filter element having a decreased pressure drop, high particulate retention properties and suitable strength.

Because of the number of sinter bonds in the filter element can be reduced, a fluid can pass through the filter element with less resistance than through a filter element having an increased number of sinter bonds. Furthermore, in some embodiments, production costs can be lowered by reducing the number of sinter bonds in a filter element. For example, a
5 filter element may be produced by coating a slurry including metal particles having a low melting and/or sintering temperature (e.g., nickel) on a porous substrate having a high melting and/or sintering temperature (e.g., stainless steel). After some of the slurry is impregnated into the pores of the porous substrate, the entire structure can be sintered at a temperature high enough to bond the inorganic particles to each other, but not high
10 enough to bond the inorganic particles to the porous substrate. The resulting filter element includes a filter medium engaged with or interlocked with the porous substrate. Since less heat can be used to join the filter medium to the substrate, less energy and consequently lower costs can be used to create a filter element. Moreover, by using lower sintering temperatures, the pores of the porous substrate are less likely to collapse or
15 deform in response to heating. Consequently, a filter element having less defects can be created.

A filter element according to embodiments of the invention can provide for advantages. For example, the porous substrate of the filter element can help structurally support the porous inorganic filter medium. This may be preferable if the porous
20 inorganic filter medium is intended to filter a high pressure fluid. Additionally, the filter element can provide for better overall filtration properties than an unsupported porous inorganic filter medium. For example, a porous substrate can serve as a prefilter for a porous inorganic filter medium with a smaller pore rating than the porous substrate.

The porous inorganic filter medium or the filter element can be used in any suitable manner. For example, the porous inorganic filter medium or the filter element can be inserted across a fluid flow path defined by a housing having any suitable construction or geometry. The porous inorganic filter medium or the filter element can be
5 joined to the housing either directly or indirectly, and by any suitable joining method. Joining methods include electron beam welding, laser welding, inert gas welding, resistance welding, soldering, and sintering. The housing can also include suitable material. Preferably, the housing is made of an inorganic material which can be joined to the porous inorganic filter medium and/or the filter element. In this regard, the material
10 used for the housing can be compatible with the material used for the porous inorganic filter medium. Exemplary housing materials include nickel and stainless steel.

The porous inorganic filter medium or the filter element can also form part of a filter cartridge or filter assembly. For example, the porous inorganic filter medium and/or filter element may be used as a separation medium of a filter cartridge or filter assembly.
15 Filter cartridges and filter assemblies according to embodiments of the invention are preferably easily replaced if they become spent.

Filter cartridges in accordance with embodiments of the invention can have any suitable form. An exemplary filter cartridge can be a self-contained separation element, provided with a porous inorganic filter medium or a filter element in tubular form, capped
20 off by end caps at one or both ends. Either or both end caps can have a through opening for fluid circulation through the porous inorganic filter medium or the filter element in either direction. End caps can be attached to the ends of the tubular porous inorganic filter medium or filter element by any suitable method including sintering or welding or in

a unitary manner as previously described. Filter cartridges in accordance with embodiments of the invention can include simple cylinders, corrugated cylinders, one or more stacked discs, etc.

Filter assemblies may include, for example, a filter element or a filter medium
5 disposed in a frame. The frame may be shaped as a parallelepiped, and the filter element or filter medium may be attached to the frame in any suitable manner (e.g., welding). If desired, the filter medium or filter element of the filter assembly can have a HEPA or ULPA rating.

The filter media, filter elements, filter cartridges, and filter assemblies according
10 to embodiments of the present invention can be used in a variety of applications. For instance, embodiments of the invention can be used to filter process fluids such as liquid polymers and hot gases. Also, since embodiments of the invention have structural stability, they can be cleaned by reverse flow cleaning processes. In these processes, a high pressure fluid stream or pulse can be directed in a direction opposite to the flow path
15 of the fluid stream being filtered. By doing so, any cake residing at the surface of the filter can be removed so that the filter can be reused for further purification.

The following description describes an exemplary method for forming a porous inorganic filter medium.

Example 1

20 A slurry is formed by mixing 1 liter of methanol and 5 grams of 934 Carbopol binder in a blender. Into this slurry mixture in sequence is blended 1.79 grams of Triton X surfactant, 80 grams of Oximide 4 μ spacer particles, 160 grams of Inco 255 nickel powder having a nominal particle size of about 2.7 μ , and 107 grams of Inco 210 nickel

powder having a nominal particle size of about 7μ . This slurry mixture is mixed in the blender until the slurry has a relatively uniform composition and the presence of pockets and/or clumps in the slurry is minimized, e.g., about 10-20 minutes. Once the slurry appears to be substantially uniform, the slurry is deposited in the cavity of a female mold

5 on a 0.5 micron Teflon membrane which rests on a screen in the female mold. The area of the female mold is about 2" by 5" and the slurry is deposited to a depth of about 0.25 inch. Once deposited, a countermold is inserted into the cavity containing the slurry. The weight of the countermold compresses the slurry against the Teflon mesh and the female mold to squeeze out some or most of the methanol. The compression of the slurry forces

10 the methanol through the mesh, screen, and a liquid outlet in the female mold. At this point, sufficient methanol is removed from the slurry so that the methanol depleted slurry is a free-standing green structure. The free-standing green structure is then removed from the mold. Additional methanol is then removed from the freestanding green structure by heating the green structure in a low temperature oven. Subsequently, the free-standing

15 green structure is placed in an oven and is heated to about 371°C in an argon atmosphere to combust the oxamide spacing agent. The combusted spacing agent creates additional pores in the free-standing green structure. The free-standing porous green structure is then placed in a sintering furnace and is fired in an atmosphere of about 60% nitrogen/40% hydrogen at about 525°C for about 60 minutes to sinter the metallic

20 particles in the free-standing, porous green structure together. After sintering the metallic particles in the porous green structure, a porous metallic filter medium is formed. The formed porous metallic filter medium has a voids volume of about 85%.

Example 2

16.3 grams of the slurry mixture of Example 1 is deposited in a mold apparatus of the type shown in Figure 2. The dies are positioned against the slurry to define a first portion, e.g., a brim portion, a second portion, e.g., a sidewall or body portion, and a third portion, e.g., an end portion. The dies are then actuated such that the dies move at a rate of about 1 inch per minute or less to provide a 55% compression ratio for each of the first, second, and third portions. The dies forming the first and third portions move through an axial displacement of about 0.080 inch to form first and third portions having a thickness of about 0.065 inch and the dies forming the second portion move through a total axial displacement of about 1.375 inches to form a second portion having an axial dimension of about 1.19 inches. This uniform compression ratio provides a uniform porosity for each of the three portions. As the pistons are moved along their axial displacement, liquid from the slurry is displaced through the gaps between the dies and between the dies and the housing. After the dies have moved through their axial displacement and the slurry has been compressed to squeeze some or most of the methanol from the slurry, the dies are retracted and the free-standing hat-shaped green structure is removed from the mold apparatus. The green structure is air dried at room temperature to remove the remaining methanol. Subsequently, the free-standing hat-shaped green structure is placed in an oven and is heated to about 371°C in an argon atmosphere to combust the oximide spacing agent. The porous structure is then placed in a sintering furnace and is fired in an atmosphere of 100% hydrogen at about 525°C for about 60 minutes to sinter the metallic particles in the free standing hat-shaped porous green structure together. Sintering the metallic particles in the porous green structure forms a

porous metallic filter medium having a porosity of about 70%.

Example 3

A slurry is formed by mixing about 1 liter DI water and 15 grams of 934 Carbopol binder in a blender. Into this slurry mixture is blended 35 grams of 1.5 micron 3-6-L stainless steel fibers. This slurry mixture is mixed in the blender until the slurry has a relatively uniform composition and the presence of pockets and/or clumps in the slurry is minimized. 148 grams of the slurry mixture is deposited in the cavity of a female mold on a 0.5 micron teflon membrane which rests, in turn, on a fine screen which rests on a coarser screen in the female mold. The inner diameter of the female mold is about 1.375 inches. A piston presses the slurry until the green structure is a 0.070 inch thick disk, removing some or most of the DI water and forming a green structure. The green disk is removed from the mold and air dried at room temperature. The dried green structure is then sintered in a hydrogen atmosphere at about 1800°F for about 30 minutes. Sintering the metallic particles in the green structure forms a porous metallic filter medium having a porosity of about 70%.

Example 4

A slurry is formed by mixing 17,250 grams of DI water and 260 grams of 941 Carbopol binder in a mixer. Ammonia is then added until the viscosity of the slurry mixture is approximately 7000 to 7500 CPS. Subsequently, 13,620 grams of Inco 255 nickel powder is added to the slurry mixture. This slurry mixture is mixed in the mixer until the slurry has a relatively uniform composition and the presence of pockets and/or clumps is minimized. The slurry is pored into a reverse roll coater and the gap between the rolls is set to 0.039 inches. A 0.0160 inch thick porous substrate available from Pall

Corporation under the trade designation PMM is directed into the reverse roll coater and the top surface of the porous substrate is coated with the slurry. The coated substrate is dried and rolled to a thickness of 0.0185 inch. The rolled, coated substrated is sheared to 66 inch lengths and formed into a loose roll. The rolls are sintered in a sintering furnace
5 at about 250°C for 75 minutes in a hydrogen atmosphere. The resulting filter medium comprises sintered nickel particles mechanically interlocked to the PMM substrate.

Any one or more of the features of any of the embodiments of the invention may be combined with any one or more of the features of any of the other embodiments without departing from the spirit and the scope of the invention. Further, while the
10 invention has been described in some detail by way of illustration and example, it is understood that the invention is not restricted to the specifically described embodiments in the specification. Rather, the invention includes all modifications, equivalents and alternatives falling within the spirit and the scope of the invention.

What is claimed is:

1. A method of forming a porous medium comprising:

applying pressure to a first portion of a medium precursor including inorganic particles;

5 separately applying pressure to a second portion of the medium precursor; and
sinter bonding the inorganic particles together.

2. A porous medium comprising:

a first portion having a first axial dimension and

10 a second portion having a second axial dimension, the second axial dimension
being greater than the first axial dimension, wherein the first and second portions each
have a predetermined porosity.

3. A porous medium comprising:

15 a porous sintered inorganic body portion having a first end and a porous sintered
inorganic end portion closing the end of the body portion, the porous body portion and the
porous end portion comprising a unitary structure.

4. A porous element comprising:

20 a porous medium of sintered inorganic particles; and

a porous substrate, at least a portion of the sintered inorganic particles being
disposed within pores of the porous substrate mechanically interlocking the porous
medium and the porous substrate.

5. A process for making a porous element comprising:

contacting a porous substrate with a slurry including a liquid medium and inorganic particles; and

5 sintering the inorganic particles together within pores of the porous substrate to mechanically interlock the sintered inorganic particles to the porous substrate.

6. A porous medium comprising:

a porous sintered inorganic structure derived from a pressed mixture including a
10 liquid medium and a plurality of inorganic particles having a nominal first size.

7. A method comprising:

applying pressure to a slurry including a liquid medium and inorganic particles;
and

15 separating at least some of the liquid medium from the slurry in response to the pressure.

8. A porous medium comprising:

a mass of sintered inorganic particles having a porosity of greater than about 50%.
20

9. A method comprising:

forming a mixture including at least a liquid medium, a plurality of inorganic particles having a nominal first size and a plurality of inorganic particles having a nominal

second size, said first size being less than the second size; and

• sinter bonding the plurality of inorganic particles having a nominal first size and the plurality of inorganic particles having a nominal second size together.

5 10. A porous medium comprising:

a first plurality of inorganic regions having a first nominal size;

a second plurality of second inorganic regions having a second nominal size,

wherein the first nominal size is less than the second nominal size, and wherein the first plurality of inorganic regions is interspersed between the second plurality of inorganic

10 regions; and

a plurality of bonds interposed between the first plurality of inorganic regions and the second plurality of inorganic regions.

11. A mold apparatus comprising:

15 a mold cavity arranged to contain a slurry;

a first die arranged to press a first portion of the slurry in the mold cavity; and

a second die arranged to separately press a second portion of the slurry in the mold cavity.

1/2




FIG. 1 (a)




FIG. 1 (b)




FIG. 2

INTERNATIONAL SEARCH REPORT

I. International Application No

PCT/US 99/19153

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01D39/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 15, no. 396, 8 October 1991 (1991-10-08) & JP 03 162503 A (ISHIKAWAJIMA), 12 July 1991 (1991-07-12) abstract ---	1-3, 6, 7, 11
X	PATENT ABSTRACTS OF JAPAN vol. 17, no. 377, 15 July 1993 (1993-07-15) & JP 05 064804 A (SINTOKOGIO), 19 March 1993 (1993-03-19) abstract ---	1, 11

-/--

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

3 February 2000

Date of mailing of the international search report

10/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Bertram, H

INTERNATIONAL SEARCH REPORT

I. International Application No

PCT/US 99/19153

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 17, no. 334, 24 June 1993 (1993-06-24) & JP 05 038098 A (SUMITOMO ELECTRIC IND), 12 February 1993 (1993-02-12) abstract ---	4,5,10
X	PATENT ABSTRACTS OF JAPAN vol. 19, no. 502, 31 March 1995 (1995-03-31) & JP 06 327920 A (TOTOKU ELECTRIC CO), 29 November 1994 (1994-11-29) abstract ---	4
X	PATENT ABSTRACTS OF JAPAN vol. 13, no. 115, 20 March 1989 (1989-03-20) & JP 63 288973 A (ISHIKAWAJIMA HARIMA HEAVY IND), 25 November 1988 (1988-11-25) abstract ---	6,7,9
X	PATENT ABSTRACTS OF JAPAN vol. 13, no. 255, 13 June 1989 (1989-06-13) & JP 01 058305 A (IBIDEN CO), 6 March 1989 (1989-03-06) abstract ---	4,10
X	EP 0 764 456 A (MORTON INTERNATIONAL, INC) 26 March 1997 (1997-03-26) claim 1; figure 2 ---	9
X	US 5 660 863 A (K.NAKANO ET AL.) 26 August 1997 (1997-08-26) figure 1; examples 1,2 -----	6,7,9

INTERNATIONAL SEARCH REPORT

Information on patent family members

I. International Application No

PCT/US 99/19153

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 03162503 A	12-07-1991	JP 2836139 B	14-12-1998
JP 05064804 A	19-03-1993	JP 2800955 B	21-09-1998
JP 05038098 A	12-02-1993	NONE	
JP 06327920 A	29-11-1994	JP 2791737 B	27-08-1998
JP 63288973 A	25-11-1988	JP 2099801 C	22-10-1996
		JP 8025813 B	13-03-1996
JP 01058305 A	06-03-1989	NONE	
EP 764456 A	26-03-1997	US 5759219 A	02-06-1998
US 5660863 A	26-08-1997	JP 2053846 C	23-05-1996
		JP 6263549 A	20-09-1994
		JP 7091121 B	04-10-1995
		JP 6320516 A	22-11-1994
		JP 8025181 B	13-03-1996
		FR 2702475 A	16-09-1994
		US 5489408 A	06-02-1996

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B01D39/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 15, no. 396, 8 October 1991 (1991-10-08) & JP 03 162503 A (ISHIKAWAJIMA), 12 July 1991 (1991-07-12) abstract	1-3, 6, 7, 11
X	<p>---</p> <p>PATENT ABSTRACTS OF JAPAN vol. 17, no. 377, 15 July 1993 (1993-07-15) & JP 05 064804 A (SINTOKOGIO), 19 March 1993 (1993-03-19) abstract</p> <p>---</p>	1, 11

-/--

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

° Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

3 February 2000

Date of mailing of the international search report

10/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bertram, H

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 17, no. 334, 24 June 1993 (1993-06-24) & JP 05 038098 A (SUMITOMO ELECTRIC IND), 12 February 1993 (1993-02-12) abstract ----	4,5,10
X	PATENT ABSTRACTS OF JAPAN vol. 19, no. 502, 31 March 1995 (1995-03-31) & JP 06 327920 A (TOTOKU ELECTRIC CO), 29 November 1994 (1994-11-29) abstract ----	4
X	PATENT ABSTRACTS OF JAPAN vol. 13, no. 115, 20 March 1989 (1989-03-20) & JP 63 288973 A (ISHIKAWAJIMA HARIMA HEAVY IND), 25 November 1988 (1988-11-25) abstract ----	6,7,9
X	PATENT ABSTRACTS OF JAPAN vol. 13, no. 255, 13 June 1989 (1989-06-13) & JP 01 058305 A (IBIDEN CO), 6 March 1989 (1989-03-06) abstract ----	4,10
X	EP 0 764 456 A (MORTON INTERNATIONAL, INC) 26 March 1997 (1997-03-26) claim 1; figure 2 ----	9
X	US 5 660 863 A (K.NAKANO ET AL.) 26 August 1997 (1997-08-26) figure 1; examples 1,2 -----	6,7,9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/19153

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 03162503 A	12-07-1991	JP 2836139 B	14-12-1998
JP 05064804 A	19-03-1993	JP 2800955 B	21-09-1998
JP 05038098 A	12-02-1993	NONE	
JP 06327920 A	29-11-1994	JP 2791737 B	27-08-1998
JP 63288973 A	25-11-1988	JP 2099801 C	22-10-1996
		JP 8025813 B	13-03-1996
JP 01058305 A	06-03-1989	NONE	
EP 764456 A	26-03-1997	US 5759219 A	02-06-1998
US 5660863 A	26-08-1997	JP 2053846 C	23-05-1996
		JP 6263549 A	20-09-1994
		JP 7091121 B	04-10-1995
		JP 6320516 A	22-11-1994
		JP 8025181 B	13-03-1996
		FR 2702475 A	16-09-1994
		US 5489408 A	06-02-1996



PATENT COOPERATION TREATY



PCT/US99/19153

PCT

NOTIFICATION OF ELECTION

(PCT Rule 61.2)

From the INTERNATIONAL BUREAU

To:

Assistant Commissioner for Patents
United States Patent and Trademark
Office
Box PCT
Washington, D.C.20231
ETATS-UNIS D'AMERIQUE

in its capacity as elected Office

Date of mailing (day/month/year) 05 May 2000 (05.05.00)	
International application No. PCT/US99/19153	Applicant's or agent's file reference 440130/PALL
International filing date (day/month/year) 24 August 1999 (24.08.99)	Priority date (day/month/year) 24 August 1998 (24.08.98)
Applicant LOVE, Charles et al	

1. The designated Office is hereby notified of its election made:

☒ in the demand filed with the International Preliminary Examining Authority on:

24 March 2000 (24.03.00)

☐ in a notice effecting later election filed with the International Bureau on:

2. The election ☒ was

☐ was not


made before the expiration of 19 months from the priority date or, where Rule 32 applies, within the time limit under Rule 32.2(b).

The International Bureau of WIPO 34, chemin des Colombettes 1211 Geneva 20, Switzerland Facsimile No.: (41-22) 740.14.35	Authorized officer Pascal Piriou Telephone No.: (41-22) 338.83.38
---	---

PATENT COOPERATION TREATY

From the
INTERNATIONAL PRELIMINARY EXAMINING AUTHORITY

To: JOHN M. BELZ
LEYDIG, VOIT & MAYER, LTD.
SUITE 300
700 THIRTEENTH STREET, N.W.
WASHINGTON DC 20005



NOTIFICATION OF TRANSMITTAL OF INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Rule 71.1)

Date of Mailing
(day/month/year)

14 DEC 2000

Applicant's or agent's file reference

440130/PALL

IMPORTANT NOTIFICATION

International application No.

PCT/US99/19153

International filing date (day/month/year)

24 AUGUST 1999

Priority Date (day/month/year)

24 AUGUST 1998

Applicant

PALL CORPORATION

1. The applicant is hereby notified that this International Preliminary Examining Authority transmits herewith the international preliminary examination report and its annexes, if any, established on the international application.
2. A copy of the report and its annexes, if any, is being transmitted to the International Bureau for communication to all the elected Offices.
3. Where required by any of the elected Offices, the International Bureau will prepare an English translation of the report (but not of any annexes) and will transmit such translation to those Offices.

4. REMINDER

The applicant must enter the national phase before each elected Office by performing certain acts (filing translations and paying national fees) within 30 months from the priority date (or later in some Offices)(Article 39(1))(see also the reminder sent by the International Bureau with Form PCT/IB/301).

Where a translation of the international application must be furnished to an elected Office, that translation must contain a translation of any annexes to the international preliminary examination report. It is the applicant's responsibility to prepare and furnish such translation directly to each elected Office concerned.

For further details on the applicable time limits and requirements of the elected Offices, see Volume II of the PCT Applicant's Guide.

Name and mailing address of the IPEA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Authorized officer

DANIEL JENKINS

Jean Proctor
Paralegal Specialist

Facsimile No. (703) 305-3230

Telephone No. (703) 306-4157

PATENT COOPERATION TREATY

PCT

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference 440130/PALL	FOR FURTHER ACTION See Notification of Transmittal of International Preliminary Examination Report (Form PCT/IPEA/416)	
International application No. PCT/US99/19153	International filing date (<i>day/month/year</i>) 24 AUGUST 1999	Priority date (<i>day/month/year</i>) 24 AUGUST 1998
International Patent Classification (IPC) or national classification and IPC IPC(7): B01D 39/20 and US Cl.: 419/2		
Applicant PALL CORPORATION		

1. This international preliminary examination report has been prepared by this International Preliminary Examining Authority and is transmitted to the applicant according to Article 36.

2. This REPORT consists of a total of 3 sheets.

☐ This report is also accompanied by ANNEXES, i.e., sheets of the description, claims and/or drawings which have been amended and are the basis for this report and/or sheets containing rectifications made before this Authority. (see Rule 70.16 and Section 607 of the Administrative Instructions under the PCT).

These annexes consist of a total of 0 sheets.

3. This report contains indications relating to the following items:

- I ☒ Basis of the report
- II ☐ Priority
- III ☐ Non-establishment of report with regard to novelty, inventive step or industrial applicability
- IV ☐ Lack of unity of invention
- V ☒ Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement
- VI ☐ Certain documents cited
- VII ☐ Certain defects in the international application
- VIII ☐ Certain observations on the international application

Date of submission of the demand 24 MARCH 2000	Date of completion of this report 06 NOVEMBER 2000
Name and mailing address of the IPEA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231	Authorized officer DANIEL JENKINS
Facsimile No. (703) 305-3230	Telephone No. (703) 306-4157

Jean Proctor
Paralegal Specialist

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

International application No.

PCT/US99/19153

I. Basis of the report

1. With regard to the elements of the international application:*

☒ the international application as originally filed☒ the description:

pages 1-40

pages NONE, as originally filed

pages NONE, filed with the demand

, filed with the letter of

☒ the claims:

pages 41-43

pages NONE, as originally filed

pages NONE, as amended (together with any statement) under Article 19

pages NONE, filed with the demand

, filed with the letter of

☒ the drawings:

pages 1-2

pages NONE, as originally filed

pages NONE, filed with the demand

, filed with the letter of

☒ the sequence listing part of the description:

pages NONE

pages NONE, as originally filed

pages NONE, filed with the demand

, filed with the letter of

2. With regard to the language, all the elements marked above were available or furnished to this Authority in the language in which the international application was filed, unless otherwise indicated under this item.

These elements were available or furnished to this Authority in the following language _____ which is:

☐ the language of a translation furnished for the purposes of international search (under Rule 23.1(b)).☐ the language of publication of the international application (under Rule 48.3(b)).☐ the language of the translation furnished for the purposes of international preliminary examination (under Rules 55.2 and/or 55.3).

3. With regard to any nucleotide and/or amino acid sequence disclosed in the international application, the international preliminary examination was carried out on the basis of the sequence listing:

☐ contained in the international application in printed form.☐ filed together with the international application in computer readable form.☐ furnished subsequently to this Authority in written form.☐ furnished subsequently to this Authority in computer readable form.☐ The statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.☐ The statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished.4. ☒ The amendments have resulted in the cancellation of:☒ the description, pages none☒ the claims, Nos. none☒ the drawings, sheets/fig none5. ☐ This report has been drawn as if (some of) the amendments had not been made, since they have been considered to go beyond the disclosure as filed, as indicated in the Supplemental Box (Rule 70.2(c)).**

* Replacement sheets which have been furnished to the receiving Office in response to an invitation under Article 14 are referred to in this report as "originally filed" and are not annexed to this report since they do not contain amendments (Rules 70.16 and 70.17).

**Any replacement sheet containing such amendments must be referred to under item 1 and annexed to this report.

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

International application No.

PCT/US99/19153

V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement**1. statement**

Novelty (N)

Claims 2, 9, 10 YESClaims 1, 3-8, 11 NO

Inventive Step (IS)

Claims none YESClaims 1-11 NO

Industrial Applicability (IA)

Claims 1-11 YESClaims none NO**2. citations and explanations (Rule 70.7)**

A. Claims 1, 3-8 and 11 lack novelty under PCT Article 33(2) as being anticipated by Nakano et al. '863.

Nakano et al. '863 discloses a method of making a porous medium, the porous medium made and the mold for forming the porous medium comprising:

providing a slurry to a mold containing a porous substrate;

pressing the slurry and porous substrate to form an impregnated porous substrate;

sintering the impregnated porous substrate to form a porous medium.

Nakano et al. '863 further discloses wherein the die has an upper portion and a lower portion.

B. Claims 2, 9 and 10 lack an inventive step under PCT Article 33(3) as being obvious over Nakano et al. '863. Nakano et al. '863 discloses the invention substantially as claimed (see A above). However, Nakano et al. does not disclose wherein the slurry comprises particles of two nominal sizes. It is common knowledge in the prior art to use powders of two nominal sizes in the same field of endeavor for the purpose of controlling porosity in different zones in a sintered substrate. It would have been obvious to one having ordinary skill in the art at the time of the invention to use two different powder sizes in the slurry of Nakano et al. '863 for the purpose of controlling porosity in the formed medium.

C. Claims 1-11 meet the criteria set out in PCT Article 33(4) as a filter media.

----- NEW CITATIONS -----

NONE

PATENT COOPERATION TREATY

0/-763597 PCT/US99/19153

PCT

From the INTERNATIONAL BUREAU

INFORMATION CONCERNING ELECTED OFFICES NOTIFIED OF THEIR ELECTION

(PCT Rule 61.3)

To:

BELZ, John, M.
Leydig, Voit & Mayer, Ltd.
700 Thirteenth Street, N.W.
Suite 300
Washington, DC 20005
ETATS-UNIS D'AMERIQUE

16 2000

Date of mailing (day/month/year) 05 May 2000 (05.05.00)		
Applicant's or agent's file reference 440130/PALL		IMPORTANT INFORMATION
International application No. PCT/US99/19153	International filing date (day/month/year) 24 August 1999 (24.08.99)	
Priority date (day/month/year) 24 August 1998 (24.08.98)		
Applicant PALL CORPORATION et al		

1. The applicant is hereby informed that the International Bureau has, according to Article 31(7), notified each of the following Offices of its election:

AP : GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW
EP : AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE
National : AU, BG, BR, CA, CN, CZ, DE, IL, JP, KP, KR, MN, NO, NZ, PL, RO, RU, SE, SK, US

2. The following Offices have waived the requirement for the notification of their election; the notification will be sent to them by the International Bureau only upon their request:

EA : AM, AZ, BY, KG, KZ, MD, RU, TJ, TM
OA : BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG
National : AE, AL, AM, AT, AZ, BA, BB, BY, CH, CR, CU, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IN, IS, KE, KG, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MW, MX, PT, SD, SG, SI, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW

3. The applicant is reminded that he must enter the "national phase" before the expiration of 30 months from the priority date before each of the Offices listed above. This must be done by paying the national fee(s) and furnishing, if prescribed, a translation of the international application (Article 39(1)(a)), as well as, where applicable, by furnishing a translation of any annexes of the international preliminary examination report (Article 36(3)(b) and Rule 74.1).

Some offices have fixed time limits expiring later than the above-mentioned time limit. For detailed information about the applicable time limits and the acts to be performed upon entry into the national phase before a particular Office, see Volume II of the PCT Applicant's Guide.

The entry into the European regional phase is postponed until 31 months from the priority date for all States designated for the purposes of obtaining a European patent.

The International Bureau of WIPO
34, chemin des Colombettes
1211 Geneva 20, Switzerland

Facsimile No. (41-22) 740.14.35

Authorized officer:

Pascal Piriou

Telephone No. (41-22) 338.83.38

From the INTERNATIONAL BUREAU

PCT

NOTICE INFORMING THE APPLICANT OF THE
COMMUNICATION OF THE INTERNATIONAL
APPLICATION TO THE DESIGNATED OFFICES

(PCT Rule 47.1(c), first sentence)

To:

BELZ, John, M.
Leydig, Voit & Mayer, Ltd.
700 Thirteenth Street, N.W.
Suite 300
Washington, DC 20005
ÉTATS-UNIS D'AMÉRIQUE

1600

Date of mailing (day/month/year) 02 March 2000 (02.03.00)		IMPORTANT NOTICE	
Applicant's or agent's file reference 440130/PALL			
International application No. PCT/US99/19153	International filing date (day/month/year) 24 August 1999 (24.08.99)	Priority date (day/month/year) 24 August 1998 (24.08.98)	
Applicant PALL CORPORATION et al			

1. Notice is hereby given that the International Bureau has communicated, as provided in Article 20, the international application to the following designated Offices on the date indicated above as the date of mailing of this Notice:
AU,CN,EP,IL,JP,KP,KR,US

In accordance with Rule 47.1(c), third sentence, those Offices will accept the present Notice as conclusive evidence that the communication of the international application has duly taken place on the date of mailing indicated above and no copy of the international application is required to be furnished by the applicant to the designated Office(s).

2. The following designated Offices have waived the requirement for such a communication at this time:
AE,AL,AM,AP,AT,AZ,BA,BB,BG,BR,BY,CA,CH,CR,CU,CZ,DE,DK,DM,EA,EE,ES,FI,GB,GD,GE,GH,
GM,HR,HU,ID,IN,IS,KE,KG,KZ,LC,LK,LR,LS,LT,LU,LV,MD,MG,MK,MN,MW,MX,NO,NZ,OA,PL,PT,
RO,RU,SD,SE,SG,SI,SK,SL,TJ,TM,TR,TT,UA,UG,UZ,VN,YU,ZA,ZW
The communication will be made to those Offices only upon their request. Furthermore, those Offices do not require the applicant to furnish a copy of the international application (Rule 49.1(a-bis)).
3. Enclosed with this Notice is a copy of the international application as published by the International Bureau on
02 March 2000 (02.03.00) under No. WO 00/10685

REMINDER REGARDING CHAPTER II (Article 31(2)(a) and Rule 54.2)

If the applicant wishes to postpone entry into the national phase until 30 months (or later in some Offices) from the priority date, a demand for international preliminary examination must be filed with the competent International Preliminary Examining Authority before the expiration of 19 months from the priority date.

It is the applicant's sole responsibility to monitor the 19-month time limit.

Note that only an applicant who is a national or resident of a PCT Contracting State which is bound by Chapter II has the right to file a demand for international preliminary examination.

REMINDER REGARDING ENTRY INTO THE NATIONAL PHASE (Article 22 or 39(1))

If the applicant wishes to proceed with the international application in the national phase, he must, within 20 months or 30 months, or later in some Offices, perform the acts referred to therein before each designated or elected Office.

For further important information on the time limits and acts to be performed for entering the national phase, see the Annex to Form PCT/IB/301 (Notification of Receipt of Record Copy) and Volume II of the PCT Applicant's Guide.

The International Bureau of WIPO 34, chemin des Colombettes 1211 Geneva 20, Switzerland	Authorized officer J. Zahra
Facsimile No. (41-22) 740.14.35	Telephone No. (41-22) 338.83.38

PATENT COOPERATION TREATY

PCT

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)

REC'D 19 DEC 2000

WIPO PCT

Applicant's or agent's file reference 440130/PALL	FOR FURTHER ACTION See Notification of Transmittal of International Preliminary Examination Report (Form PCT/IPEA/416)	
International application No. PCT/US99/19153	International filing date (day/month/year) 24 AUGUST 1999	Priority date (day/month/year) 24 AUGUST 1998
International Patent Classification (IPC) or national classification and IPC IPC(7): B01D 39/20 and US Cl.: 419/2		
Applicant PALL CORPORATION		

1. This international preliminary examination report has been prepared by this International Preliminary Examining Authority and is transmitted to the applicant according to Article 36.

2. This REPORT consists of a total of 3 sheets.

☐ This report is also accompanied by ANNEXES, i.e., sheets of the description, claims and/or drawings which have been amended and are the basis for this report and/or sheets containing rectifications made before this Authority. (see Rule 70.16 and Section 607 of the Administrative Instructions under the PCT).

These annexes consist of a total of 0 sheets.

3. This report contains indications relating to the following items:

- I ☒ Basis of the report
- II ☐ Priority
- III ☐ Non-establishment of report with regard to novelty, inventive step or industrial applicability
- IV ☐ Lack of unity of invention
- V ☒ Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement
- VI ☐ Certain documents cited
- VII ☐ Certain defects in the international application
- VIII ☐ Certain observations on the international application

Date of submission of the demand 24 MARCH 2000	Date of completion of this report 06 NOVEMBER 2000
Name and mailing address of the IPEA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231	Authorized officer DANIEL JENKINS Jean Prost Paralegal Specialist
Facsimile No. (703) 305-3230	Telephone No. (703) 306-4157

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

International application No.

PCT/US99/19153

I. Basis of the report

1. With regard to the elements of the international application:*

☒ the international application as originally filed☒ the description:

pages 1-40 , as originally filed
pages NONE , filed with the demand
pages NONE , filed with the letter of _____

☒ the claims:

pages 41-43 , as originally filed
pages NONE , as amended (together with any statement) under Article 19
pages NONE , filed with the demand
pages NONE , filed with the letter of _____

☒ the drawings:

pages 1-2 , as originally filed
pages NONE , filed with the demand
pages NONE , filed with the letter of _____

☒ the sequence listing part of the description:

pages NONE , as originally filed
pages NONE , filed with the demand
pages NONE , filed with the letter of _____

2. With regard to the **language**, all the elements marked above were available or furnished to this Authority in the language in which the international application was filed, unless otherwise indicated under this item.

These elements were available or furnished to this Authority in the following language _____ which is:

- ☐ the language of a translation furnished for the purposes of international search (under Rule 23.1(b)).
☐ the language of publication of the international application (under Rule 48.3(b)).
☐ the language of the translation furnished for the purposes of international preliminary examination (under Rules 55.2 and/or 55.3).

3. With regard to any **nucleotide and/or amino acid sequence** disclosed in the international application, the international preliminary examination was carried out on the basis of the sequence listing:

- ☐ contained in the international application in printed form.
☐ filed together with the international application in computer readable form.
☐ furnished subsequently to this Authority in written form.
☐ furnished subsequently to this Authority in computer readable form.
☐ The statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.
☐ The statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished.

4. ☒ The amendments have resulted in the cancellation of:

- ☒ the description, pages none
☒ the claims, Nos. none
☒ the drawings, sheets/fig none

5. ☐ This report has been drawn as if (some of) the amendments had not been made, since they have been considered to go beyond the disclosure as filed, as indicated in the Supplemental Box (Rule 70.2(c)).**

* Replacement sheets which have been furnished to the receiving Office in response to an invitation under Article 14 are referred to in this report as "originally filed" and are not annexed to this report since they do not contain amendments (Rules 70.16 and 70.17).

**Any replacement sheet containing such amendments must be referred to under item 1 and annexed to this report.

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

International application No.

PCT/US99/19153

V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement**1. statement**

Novelty (N)	Claims <u>2, 9, 10</u>	YES
	Claims <u>1, 3-8, 11</u>	NO
Inventive Step (IS)	Claims <u>none</u>	YES
	Claims <u>1-11</u>	NO
Industrial Applicability (IA)	Claims <u>1-11</u>	YES
	Claims <u>none</u>	NO

2. citations and explanations (Rule 70.7)

A. Claims 1, 3-8 and 11 lack novelty under PCT Article 33(2) as being anticipated by Nakano et al. '863.

Nakano et al. '863 discloses a method of making a porous medium, the porous medium made and the mold for forming the porous medium comprising:

- providing a slurry to a mold containing a porous substrate;
- pressing the slurry and porous substrate to form an impregnated porous substrate;
- sintering the impregnated porous substrate to form a porous medium.

Nakano et al. '863 further discloses wherein the die has a upper portion and a lower portion.

B. Claims 2, 9 and 10 lack an inventive step under PCT Article 33(3) as being obvious over Nakano et al. '863. Nakano et al. '863 discloses the invention substantially as claimed (see A above). However, Nakano et al. does not disclose wherein the slurry comprises particles of two nominal sizes. It is common knowledge in the prior art to use powders of two nominal sizes in the same field of endeavor for the purpose of controlling porosity in different zones in a sintered substrate. It would have been obvious to one having ordinary skill in the art at the time of the invention to use two different powder sizes in the slurry of Nakano et al. '863 for the purpose of controlling porosity in the formed medium.

C. Claims 1-11 meet the criteria set out in PCT Article 33(4) as a filter media.

----- NEW CITATIONS -----

NONE

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/19153

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B01D39/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 15, no. 396, 8 October 1991 (1991-10-08) & JP 03 162503 A (ISHIKAWAJIMA), 12 July 1991 (1991-07-12) abstract	1-3,6,7, 11
X	PATENT ABSTRACTS OF JAPAN vol. 17, no. 377, 15 July 1993 (1993-07-15) & JP 05 064804 A (SINTOKOGIO), 19 March 1993 (1993-03-19) abstract	1,11
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

3 February 2000

Date of mailing of the international search report

10/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bertram, H

INTERNATIONAL SEARCH REPORT

I. International Application No

PCT/US 99/19153

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 17, no. 334, 24 June 1993 (1993-06-24) & JP 05 038098 A (SUMITOMO ELECTRIC IND), 12 February 1993 (1993-02-12) abstract	4,5,10
X	PATENT ABSTRACTS OF JAPAN vol. 19, no. 502, 31 March 1995 (1995-03-31) & JP 06 327920 A (TOTOKU ELECTRIC CO), 29 November 1994 (1994-11-29) abstract	4
X	PATENT ABSTRACTS OF JAPAN vol. 13, no. 115, 20 March 1989 (1989-03-20) & JP 63 288973 A (ISHIKAWAJIMA HARIMA HEAVY IND), 25 November 1988 (1988-11-25) abstract	6,7,9
X	PATENT ABSTRACTS OF JAPAN vol. 13, no. 255, 13 June 1989 (1989-06-13) & JP 01 058305 A (IBIDEN CO), 6 March 1989 (1989-03-06) abstract	4,10
X	EP 0 764 456 A (MORTON INTERNATIONAL, INC) 26 March 1997 (1997-03-26) claim 1; figure 2	9
X	US 5 660 863 A (K.NAKANO ET AL.) 26 August 1997 (1997-08-26) figure 1; examples 1,2	6,7,9

INTERNATIONAL SEARCH REPORT

Information on patent family members

I. International Application No

PCT/US 99/19153

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 03162503 A	12-07-1991	JP 2836139 B	14-12-1998
JP 05064804 A	19-03-1993	JP 2800955 B	21-09-1998
JP 05038098 A	12-02-1993	NONE	
JP 06327920 A	29-11-1994	JP 2791737 B	27-08-1998
JP 63288973 A	25-11-1988	JP 2099801 C	22-10-1996
		JP 8025813 B	13-03-1996
JP 01058305 A	06-03-1989	NONE	
EP 764456 A	26-03-1997	US 5759219 A	02-06-1998
US 5660863 A	26-08-1997	JP 2053846 C	23-05-1996
		JP 6263549 A	20-09-1994
		JP 7091121 B	04-10-1995
		JP 6320516 A	22-11-1994
		JP 8025181 B	13-03-1996
		FR 2702475 A	16-09-1994
		US 5489408 A	06-02-1996

PCT

INTERNATIONAL SEARCH REPORT

(PCT Article 18 and Rules 43 and 44)

Applicant's or agent's file reference 440130/PALL	FOR FURTHER ACTION see Notification of Transmittal of International Search Report (Form PCT/ISA/220) as well as, where applicable, item 5 below.	
International application No. PCT/US 99/ 19153	International filing date (day/month/year) 24/08/1999	(Earliest) Priority Date (day/month/year) 24/08/1998
Applicant PALL CORPORATION et al.		

This International Search Report has been prepared by this International Searching Authority and is transmitted to the applicant according to Article 18. A copy is being transmitted to the International Bureau.

This International Search Report consists of a total of 4 sheets.



It is also accompanied by a copy of each prior art document cited in this report.

1. Basis of the report

- a. With regard to the **language**, the international search was carried out on the basis of the international application in the language in which it was filed, unless otherwise indicated under this item.



the international search was carried out on the basis of a translation of the international application furnished to this Authority (Rule 23.1(b)).

- b. With regard to any **nucleotide and/or amino acid sequence** disclosed in the international application, the international search was carried out on the basis of the sequence listing :



contained in the international application in written form.



filed together with the international application in computer readable form.



furnished subsequently to this Authority in written form.



furnished subsequently to this Authority in computer readable form.



the statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.



the statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished

2. ☐ **Certain claims were found unsearchable** (See Box I).

3. ☐ **Unity of invention is lacking** (see Box II).

4. With regard to the **title**,



the text is approved as submitted by the applicant.



the text has been established by this Authority to read as follows:

5. With regard to the **abstract**,



the text is approved as submitted by the applicant.



the text has been established, according to Rule 38.2(b), by this Authority as it appears in Box III. The applicant may, within one month from the date of mailing of this international search report, submit comments to this Authority.

6. The figure of the **drawings** to be published with the abstract is Figure No.



as suggested by the applicant.



because the applicant failed to suggest a figure.



because this figure better characterizes the invention.

1a



None of the figures.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 99/ 19153

Box III TEXT OF THE ABSTRACT (Continuation of item 5 of the first sheet)

A porous element is produced from a slurry of inorganic (metallic) particles. Part of the liquid is removed by compression followed by drying and sintering the green body. The product is usable as inorganic filter medium.